




# CSFC TAIWAN ENTERPRISE CORPORATION

Sales Office: 3F, No. 14, Cuizhu N. Rd., Yangzhong, Jiangsu, China  
TEL:+86-511-88365501; FAX: +86-511-88350971  
Web: [www.csfchem.com](http://www.csfchem.com)

## CSFC 1130 Specification

<b>Chemical Name</b>	1. CAS 104810-48-2                      40%~55%
	a-[3-[3-(2H-Benzotriazol-2-yl)-5-(1,1-dimethylethyl)-4-hydroxyphenyl]-1-oxopropyl]-ω-hydroxypoly(oxo-1,2-ethanediyl);
	2. CAS 104810-47-1                      30~45%
<b>Molecular Formula</b>	a-[3-[3-(2H-Benzotriazol-2-yl)-5-(1,1-dimethylethyl)-4-hydroxyphenyl]-1-oxopropyl]-ω-[3-[3-(2H-benzotriazol-2-yl)-5-(1,1-dimethylethyl)-4-hydroxyphenyl]-1-oxopropoxy]poly(oxy-1,2-ethanediyl);
	3. CAS 25322-68-3                      10~16%
<b>Molecular Weight</b>	Polyethyleneglycol 300
<b>Molecular Formula</b>	$C_{19}H_{21}N_3O_3 \cdot (C_2H_4O)_n$ , n=6-7
<b>Molecular Weight</b>	A: 637; B: 975; C: 300



<b>CAS Number</b>	A:104810-48-2; B: 104810-47-1; C: 25322-68-3
-------------------	--

<b>Specification</b>	Appearance:	Yellow to light amber viscous liquid
	Dynamic Viscosity(20°C) (mPa.s)	7400±2.0
	Density(20°C) g/cm3	1.17
	Loss on drying %	0.5 max
	Transmittance %	460nm 95.0 min 500nm 97.0 min

<b>Packing</b>	25kg/plastic drum
----------------	-------------------

**Applications** CSFC 1130 is recommended for both solvent and water based coatings

